

**RatnerPrestia**

WE SPECIALIZE IN THE LAW OF CREATIVITY®

**RECEIVED
CENTRAL FAX CENTER****SEP 26 2006**

☒
Suite 301, One Westlakes, Berwyn
P.O. Box 980
Valley Forge, PA 19482-0980
Phone: 610-407-0700
Fax: 610-407-0701

☐
Nemours Building
1007 Orange Street, Suite 1100
P.O. Box 1596
Wilmington, DE 19899
Phone: 302-778-2500
Fax: 302-778-2600

www.ratnerprestia.com

☐
Suite 265
Commerce Corporate Center
5100 Tilghman Street
Allentown, PA 18104
Phone: 610-530-8100
Fax: 610-530-8200

F A C S I M I L E C O V E R S H E E TDATE: September 26, 2006OUR REF.: ANMS-129US

TIME: _____

YOUR REF.: 10/692,761

TO:	Examiner Kallambella Vijayakumar
COMPANY:	U.S. Patent & Trademark Office
FROM:	Jacques L. Etkowicz, Esq. and Stephen E. Johnson Ph.D.
FAX TELEPHONE:	571-273-8300
OFFICE TELEPHONE:	571-272-1324
TITLE OF DOCUMENT:	DRAFT Amended Claim for 10/692,761

Total Number of Pages: 2 (including this form)

COMMENTS

Enclosed is the DRAFT amended claim we discussed yesterday. Please let us know if this addresses your concerns by calling us at 610-993-4205 or 610-993-4247.

Thank you.

CONFIDENTIAL AND PRIVILEGED ATTORNEY/CLIENT INFORMATION

This facsimile transmission (and/or documents accompanying it) may contain attorney/client privileged communications and confidential business information that is intended for use only by the individual or company to whom it is addressed. Disclosure, interception, copying or any other use of this transmission by anyone other than any intended recipient is prohibited. If you receive this transmission by mistake, please notify the sender.

Please notify us immediately if you have not received the number of pages indicated above.

Appln. No.: 10/692,761

ANMS-129US

RECEIVED
CENTRAL PAX CENTER
SEP 26 2006

21. (Currently Amended) A conductive polymer composition comprising:

about 0.01% to about 5% by weight of a transition metal catalyst;

an electrically conductive material; and

a polymer binder comprising acrylic acid/acrylate copolymers or acrylic acid/acrylate/acrylic acid terpolymers prepared by polymerizing monomers selected from the group consisting of: alkyl acrylates, alkyl methacrylates, hydroxyl-alkyl acrylates, hydroxyl-alkyl methacrylates, acrylic acid, methacrylic acid, carboxyl alkyl acrylates, carboxyl methacrylates, amino alkyl acrylate, amino alkyl methacrylate, vinylamine acrylate and vinyl amine alkyl acrylate.